

Perspex® Cell Cast Acrylic

Technical Data Sheet

1. Range

Perspex® cell cast acrylic sheet is available in clear, opal and many colours in a range of thicknesses, sizes and special grades.

2. Masking

Perspex® sheet is supplied with double-sided, non-thermoformable masking. The showface masking is printed with the Perspex® logo.

3. Table of Properties

Values quoted for the properties of Perspex® cast sheet are the results of tests on representative samples and do not constitute specifications.

Property	Test Method	Unit	Value
General			
Density	ISO 1183	g cm ⁻³	1.19
Rockwell Hardness	ISO 2039-2	M scale	102
Water Absorption	ISO 62	%	0.2
Flammability	BS 476 Part 7	Class	3
	DIN 4102	-	B2
	NFP 92-507	-	M4
	UL94	-	HB
	ISO 11925-2	-	E
Optical Properties			
Light Transmission	ASTM D1003	% (3 mm)	> 92
Refractive Index	ISO 489 A	-	1.49
Thermal Properties			
Vicat Softening Point	ISO 306 A	°C	> 110
Coefficient of Thermal Expansion (Linear)	ASTM D696	x 10 ⁻⁵ . K ⁻¹	7.7
Mechanical Properties			
Tensile Strength	ISO 527 (5 mm/min)	MPa	75
Elongation at Break	ISO 527 (5 mm/min)	%	4
Flexural Strength	ISO 178 (2 mm/min)	MPa	116
Flexural Modulus	ISO 178 (2 mm/min)	MPa	3210
Impact Strength – Charpy (unnotched)	ISO 179	kJ M ⁻²	12
Poisson's Ratio	ISO 179	kJ M ⁻²	0.38
Electrical Properties			
Surface Resistivity	IEC 93	Ω.m-2	> 10 ¹⁴
Electrical Strength	IEC 243	kV.mm-1	15

Perspex® is a registered trademark of the Lucite International UK Limited (registered in England No 3830161) group of Companies.

Perspex® Cast Acrylic Sheet

The information given in this report is confidential. Its reproduction in whole, in part or in summary form without our written consent in each instance is expressly forbidden. The information is given in good faith and is based on our general experience, but because of the many particular factors which are outside our knowledge and control that affect the use of products, no warranty is given or is to be implied. Freedom from patent rights must not be assumed.

